

Sani-Tech®

Silicone Stoppers

Sani-Tech® Silicone Stoppers

Sani-Tech® ultra-pure, platinum-cured silicone stoppers outperform standard neoprene and rubber stoppers in critical process and laboratory applications in terms of life expectancy, consistency, and purity. Sani-Tech® silicone stoppers are fully autoclavable and sterilizable and will not crack, cause spallation, or release particulates that could cause process contamination or lost product.

Sani-Tech® silicone stoppers can be supplied with cored holes for use with specially designed dip tubes or vent configurations. Custom identification markings can also be utilized to help differentiate supply lines.

Characteristics

The manufacturing process is carefully controlled from receiving through production and inspection and lot traceability is readily accessible in all stages through batch number assignments.

Saint-Gobain Performance Plastics ISO 9001 manufacturing facilities have the ability to create a wide variety of customized silicone stoppers including color coding and coring options to fit the demanding applications of the pharmaceutical, biotechnology, and laboratory environments.

Biocompatibility

Sani-Tech® ultra-pure silicone stoppers are manufactured from a biopharmaceutical grade of silicone materials and are fully characterized from a biological, chemical, and physical standpoint. Sani-Tech® stoppers are tested to specifications including FDA 177.2600 criteria and meets the requirements of USP <88> Class VI, and/or USP <87>, and/or ISO 10993-5. Sani-Tech® ultra-pure silicone stoppers have a masterfile with the U.S Food and Drug Administration.


Features / Benefits

- Ultra-pure biopharmaceutical grade silicone
- Unsurpassed surface smoothness
- Resists cracking and spallation
- No particle migration
- Fully autoclavable and sterilizable
- Imparts no taste or odors
- Biologically safe
- Custom identification and color options

Typical Applications

- Carboys and vessels
- Solution and media bottles
- Process and storage procedures
- Laboratory apparatus

Sani-Tech® Silicone Stoppers Selection Guide



Part Number	Size	A Inches (mm)	B Inches (mm)	H Inches (mm)	Volume Inches* (cm*)	Weight LB (G)
4120-1000	000	0.528 (13.4)	0.350 (8.9)	0.830 (21.1)	0.127 (2.08)	0.005 (2.27)
4120-1100	00	0.593 (15.1)	0.421 (10.7)	0.980 (24.9)	0.195 (3.20)	0.008 (3.63)
4120-1110	0	0.665 (16.9)	0.518 (13.2)	0.981 (24.9)	0.272 (4.46)	0.012 (5.44)
4120-1001	1	0.776 (19.7)	0.587 (14.9)	0.970 (24.6)	0.342 (5.60)	0.015 (6.8)
4120-1002	2	0.773 (19.6)	0.637 (16.2)	0.989 (25.1)	0.393 (6.44)	0.017 (7.71)
4120-1003	3	0.950 (24.1)	0.725 (18.4)	0.982 (24.9)	0.544 (8.91)	0.023 (10.43)
4120-1004	4	1.029 (26.1)	0.779 (19.8)	0.975 (24.7)	0.628 (10.29)	0.026 (11.79)
4120-1005	5	1.051 (26.7)	0.890 (22.6)	0.968 (24.6)	0.744 (12.19)	0.031 (14.06)
4120-1006	6	1.256 (31.9)	1.041 (26.4)	0.915 (23.2)	0.947 (15.52)	0.040 (18.14)
4120-1007	7	1.440 (36.6)	1.115 (28.3)	0.957 (24.3)	1.233 (20.2)	0.054 (24.49)
4120-1008	8	1.611 (41.0)	1.305 (33.2)	0.991 (25.2)	1.664 (27.3)	0.073 (33.11)
4120-1009	9	1.775 (45.1)	1.474 (37.4)	0.987 (25.1)	2.052 (33.63)	0.086 (39.01)
4120-1010	10	1.973 (50.1)	1.669 (42.4)	0.935 (23.7)	2.425 (39.74)	0.102 (26.27)
4120-1011	11	2.187 (55.5)	1.913 (48.6)	0.941 (23.9)	3.137 (51.41)	0.032 (59.88)
4120-1012	12	2.508 (63.7)	2.134 (54.2)	0.965 (24.5)	4.253 (69.69)	0.188 (85.28)
4120-1013	13	2.667 (67.7)	2.284 (58.0)	1.011 (25.7)	4.813 (78.87)	0.207 (93.90)
4120-1014	14	3.489 (88.6)	2.953 (75.0)	1.494 (37.9)	12.504 (204.90)	0.538 (244.04)
4120-0015	15	4.053 (102.9)	3.260 (82.8)	1.505 (38.2)	15.866 (260.00)	0.682 (309.36)
4120-0016	16	4.950 (125.7)	3.543 (90.0)	2.016 (51.2)	29.106 (476.96)	1.252 (567.91)

¹All stoppers can be supplied with cored holes for use with dip tubes, vents, etc.

²Consult factory for available sizes. Certain half and non-standard sizes are available upon request.

Sterilization Methods

Autoclavable

Radiation- up to 2.5 Mrad (25 Kilogray)

Gas -Ethylene Oxide

Typical Physical Properties

Property	ASTM Method	Value or Rating
Durometer Hardness, Shore A, 15 Sec	D2240	45
Tensile Strength, psi (MPa) 1,250	D412	
Ultimate Elongation, 100%	D412	650
Tear Resistance, lb-f/inch (kN/m)	D624	230
Specific Gravity	D792	1.12
Tensile Modulus	D412	175

Contact us today for:

Consultations • Samples • Quotes • Orders

For registered access to Saint-Gobain Product Validation Summaries,
[CLICK HERE](#)



Saint-Gobain Performance Plastics

3910 Terry-Diane Street
Beaverton, MI 48612
Tel: (888) 387-0067
Tel: (989) 435-9533
Fax: (989) 435-2355

Saint-Gobain Performance Plastics

La Mothe-aux-Aulnais
F-89120 Charny, France
Tel: (33) 3-86-63-78-78
Fax: (33) 3-86-63-77-77

www.biopharm.saint-gobain.com

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable medical regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 12 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product to be free of defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof.

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.